



Wiser With Energy

Technical Data Sheet

V200121

4EVERblue



Liquisol bv Noorderlaan 147 B9,2030 Antwerp, Belgium
VAT: BE0648.867.048 tel: 00 32 32 56 01 72 verf@liquisol.com
In case of online-purchase conflict: <http://ec.europa.eu/consumers/odr>



4EVERblue is a solar reflective water based acrylic coating to be applied on the outside of skylights, sky domes and conservatory roofs. Surfaces can be acrylic (PMMA), polycarbonate, polyester or glass. It reflects IR heat radiation and blocks solar glare. All UV-radiation is absorbed.



Before application, clean the surface with s00p SC. Check the attachment on the specific surface with the ISO 2409:2007 cross-cut test. [Click here to see the "how to install" movie.](#)



For convenience, 4EVERblue is packaged in a plastic pouch with a screwtop. It must be stored between 4°C/39°F and 30°C/86°F, and keep out of direct sunlight. 4EVERblue must used within 6 months of opening or 2 years after purchase.
EAN code 1 liter= 5425027116216. EAN code 5 liter = 5425027116254

Per litre, 4EVERblue covers an area of 8 to 9 m² or 86 to 96 ft².
1 liter = 8 to 9 m² = 86 to 96 ft². 5 liter = 40 to 45 m² = 430 to 485 ft²



Wear protective clothing when applying 4EVERblue. When spraying 4EVERblue, you should wear a mask with a combination filter safety class A/P2 or more. Gloves and overalls should also be worn. The EU limit for 4EVERblue is (Klasse A/i) : 2010: 140g/ litre. VOC level is 50g/ litre. Read the MSDS for more information.



Authorized Liquisol Applicator can give 5 years factory warranty. At at correct installation, a lifetime of 8 to 10 year can be expected.



You should use a rough brush + s00p SC + clean water + wiper + 8 mm paint roller or airless spay machine with nozzle 615 at pressure 160 bar (WSB PS3.20)

Apply at min 10°C/50°F , relative humidity = max 80% Surface temperature = min 10°C/50°F- max 35°C/95°F. Do not apply in full sunlight or when there is a high risk of rain or damp. Rainproof in 1.5h at 20°C/68°F and 65% RH (relative humidity)



Fraunhofer test rapport: Bericht – Nr.: PH031/10
Total Solar energy rejection: 57%
Visual Light Transmission: 47%
UV block: 99%

Fraunhofer

Fraunhofer